

PRODUCT DATASHEET

LEXAN™ FR700 FILM

DESCRIPTION

LEXAN™ FR700 is a black, one side fine matt, one side velvet flame-retardant polycarbonate film with a UL94 V-0 listing at 0.250 mm. This film has formability, excellent mechanical properties, good dimensional stability at high temperatures and a high flammability rating, making it good for applications such as power supply insulation, disc drive insulation, bus-bar insulation, TV/monitor insulation, PC board insulation, business equipment insulation and has insulation and EMI/RFI shielding when laminated with metal foil.

TYPICAL PROPERTY VALUES*

PROPERTY	ASTM TEST METHOD	UNITS (USCS)	VALUE	ISO TEST METHOD	UNITS (SI)	VALUE
MECHANICAL						
Tensile Strength @ Yield (0.43mm)	ASTM D882	psi	8845	ISO 527	MPa	61
Ultimate(0.43mm)	ASTM D882	psi	9470	ISO 527	MPa	66
Tensile Modulus (0.43mm)	ASTM D882	psi	379465	ISO 527	MPa	2617
Tensile Elongation at Break (0.43MM)	ASTM D882	%	41	ISO 527	%	41
Gardner Impact Strength at 0.03" (0.75mm)	ASTM D3029	ft-lb	11	ISO 6603-1	J	28
Tear Strength						
Initiation	ASTM D1004	lb/mil	1.43		kN/m	298
Propagation	ASTM D1922	g/mil	18.8		kN/m	16
Puncture Resistance (Dynatup)	ASTM D3763	ft-lb	9		J	12
Fold Endurance (MIT)						
0.010" (0.25 mm)	ASTM D2176-69	double folds	27			
0.020" (0.50 mm)	ASTM D2176-69	double folds	12			
THERMAL						
Coefficient of Thermal Conductivity	ASTM D5470	Btu/hr/ft ² /°F/in	1.35		W/m ² K	0.2
Coefficient of Thermal Expansion	ASTM E831	(x10 ⁻⁵ /°F)	3.2	ISO 11359	(x10 ⁻⁵ /°C)	5.8
Specific Heat @40°F (4°C)	ASTM E1269	Btu/lb/°F	0.3		KJ/Kg-°C	1.25
Glass Transition Temperature	ASTM D3417 / D3418	°F	307	ISO 11357	°C	153
Vicat Softening Temperature, B	ASTM 1525-00 modified	°F	347			175
Heat Deflection Temp. by TMA at 1.8 Mpa		°F	290	ISO 75 Modified	°C	145
Shrinkage at 302°F (150°C)	ASTM D1204	%	0.02		%	0.02
Brittleness Temperature	ASTM D746	°F	-211		°C	-135

PRODUCT DATASHEET

PROPERTY	ASTM TEST METHOD	UNITS (USCS)	VALUE	ISO TEST METHOD	UNITS (SI)	VALUE
PHYSICAL						
Density	ASTM D792	slug/ft ³	2.6	ISO 1183	kg/m ³	1344
Water Absorption, 24 hrs.	ASTM D570	% change	0.28	ISO 62	% change	0.28
Surface Energy(1 st surface/ 2 nd surface)	ASTM D5946-01	-	35/35			
Surface Tension(1 st surface/ 2 nd surface)	Dyne Pens	Dyne	36-38/36-38			
OPTICAL						
Gloss over Flat Black min/max @ 60°	ASTM D523-60	-	10.5	ISO 2813	-	10.5
ELECTRICAL						
Dielectric Strength in oil, short time @ 72°F (23°C), 10mils (0.25 mm)	ASTM D149-97a Method A	kv/mil	1.5	IEC 60243	kv/mm	59
Dielectric Constant						
@ 60 Hz	ASTM D150	-	2.9	IEC 60250	-	2.9
@ 1 MHz	ASTM D150	-	2.8	IEC 60250	-	2.8
Dissipation Factor						
@ 60 Hz	ASTM D150	-	0.0026	IEC 60250	-	0.0026
@ 1 MHz	ASTM D150	-	0.0117	IEC 60250	-	0.0117
Volume Resistivity	ASTM D257	Ω-cm	1.00E+17	IEC 60093	Ω-cm	1.00E+17
Surface Resistivity	ASTM D257	Ω /square	1.00E+16	IEC 60093	Ω /square	1.00E+16
Arc Resistance, Tungsten Electrodes	ASTM D495	s	64			

- ◆ These are typical properties and are not intended for specification purposes. If minimum certifiable properties are required, please contact your local POLYVANTIS representative or the POLYVANTIS Quality Services Department. Reported values are based on 0.250 mm (0.010") thickness film unless otherwise noted.

MANUFACTURING SPECIFICATIONS

NOMINAL GAUGE RANGES	MIN./MAX LIMIT OF NOMINAL
0.010 - 0.014" (0.250 - 0.350mm)	-/+ 10%
0.015 - 0.030" (0.375 - 0.750mm)	-/+ 5%

Color Code: Black Color 701 (BK)

UL FILE NUMBERS: [E539257](#), [E539253](#), [E539252](#)

POLYVANTIS

Galaxy East Industrial Park
No. 1 Dongyao Street,
Room 1702, 17th Floor, Building C
511455 Nansha District, Guangzhou
Guangdong, PRC
China
T +86-20-28666168
E info.lexan@polyvantis.net

www.polyvantis.com

